

LINITOP®

LINITOP CLASSIC

Decorative protective woodstain



INTERIOR
EXTERIOR

Priority to wood

Description	Transparent, decorative, protective woodstain, with a "high solid content" for indoor and outdoor wood with stable dimensions.
Classification	Family 1 - Class 4a (according to classifications NBT 22-003 and NFT 36-005).
Properties	<ul style="list-style-type: none"> • High solid content: double protection per coat for long term resistance. • Thixotropic formula: gelified product for better holding to the brush. Very easy to apply, does not run, for perfect flow characteristics. • Transparent: embellishes the wood and preserves its natural appearance. • Extra-flexible film, limits the risks of flaking. • Special anti-UV pigmentation for optimum protection. • Excellent resistance to bad weather.
Basic uses	<ul style="list-style-type: none"> • Indoor and outdoor vertical surfaces. • Protects and decorates wooden doors, door and window frames, beams, panelling,... <p>Except Red Cedar and wood types containing an anti-oxidant (e.g.: Iroko). Avoid wood types rich in resins.</p>
Characteristics	<ul style="list-style-type: none"> • Composition: Urethane alkyd, alkyd resins • Density (at +20°C): 0.954 ± 0.05. • Flash point: > 60°C. • Viscosity: Thixotropic. • Solid content: 60% ± 2. • VOC: EU limit value for this product (cat A/e): 400 g/l (2010). This product contains a maximum of 400 g/l VOC. <p>0.5 l - 1 l - 2.5 l - 5 l and 10 l. At least 2 years in the unused closed original packaging. Keep away from frost and high temperatures. Thixotropic liquid.</p> <p>Satin/matt.</p> <ul style="list-style-type: none"> • Packaging: • Shelf life: • Storage conditions: • Appearance in the can: • Appearance of the dry product: • Colours: • Tools: Brush, roller, spray gun. • Dilution: Ready to use. • Cleaning of the tools: White spirit. • Conditions of application: Respect the conditions and instructions stipulated by the manufacturer. Do not apply at an ambient temperature of less than +10°C or greater than +30°C. Relative humidity: 50%. 12 to 16 m²/l. - Dust-dry: 5 h. - Recoatable: 24 h. • Coverage: • Drying (data at +20°C and 50% relative humidity): • Safety: Refer to the safety data sheet and the text given on the packaging, in accordance with the applicable legislation.

The information set out consists of purely illustrative and are not the responsibility of the manufacturer, the application of products not made under his supervision.

Priority to Wood

Surface preparation

- Use on wood whose usage, nature, quality, treatments and preparation comply with the applicable standards and DTU (DTU 59.1).
The inspection and preparation of the surface are the responsibility of the user.
- The wood must be dry, clean, in sound condition, free of millglaze and properly prepared (degrease, sand, dust off).

On new wood:

- Sand (grit 120) to encourage and optimise the opening of the pores.
- Use on already stained wood is possible provided that the existing woodstain is in a good condition. However, the entire surface will have to be meticulously sanded (grit 220).

On old wood, where the existing woodstain is in a poor condition:

- Make the surface bare by sanding or stripping the entire surface.

NB: After sanding, always carefully dust the surface.

Recommendations before application

- Ready to use. Shake well before application.
 - Do not apply at an ambient air and wood temperature of less than +10°C and greater than +30°C. The relative humidity will be of the order of 50% for optimum drying.
 - Complies with the applicable standards and DTU.
 - Protect everything that does not have to be treated.
 - The moisture of the wood must not be greater than 15%.
- NB:** To protect the wood against UV, do not use «colourless» or «white» by itself outside as the finish coat. Always finish with 2 coloured coats.

Directions for use

According to the condition of the surface:

New wood or restored to new after stripping or sanding:

- Apply a coat of Linitop Prim & Finish**.
- After fully drying, end with two coats of Linitop Classic*.

Greyed wood:

- Clean with Wood Cleaner**.
- Sand (grit 120) if necessary.
- On a clean and dry surface, apply a coat of Linitop Prim & Finish** then two coats of Linitop Classic*.

Darkened oiled wood:

- Remove the oil with the Wood Oil Cleaner** + Wood Cleaner** system.
- Sand (grit 120) if necessary.
- On a clean and dry surface, apply a coat of Linitop Prim & Finish** then two coats of Linitop Classic*.

Wood to be stripped: consult us.

Indoors, all woods:

• Softwoods (resinous):

- Apply 1 to 2 coats of Linitop Classic.

• Hardwoods:

- Apply 2 to 3 coats of Linitop Classic.

An additional coat may be required depending on the absorption of the wood and the desired appearance.

Advice of the professionals

- Always apply Linitop Classic in the direction of the wood fibres.
- On new wood or wood made bare, that is not durable and has not been treated with a preservative, it is recommended first treating it with an insecticide, fungicide and anti-blue stain agent. Consult us.
- During application, pay particular attention to grooves and butts.
- When working with a spray gun, smooth with a brush to avoid any running and to aid the penetration of the product.

Maintenance

Usual restoration:

- Apply one or two coats of Linitop Classic* according to the condition of the coating after brushing or sanding.

Restoration on a highly damaged surface:

- Make the wood bare by sanding or stripping, then apply a coat of Linitop Prim & Finish** and 2 coats of Linitop Classic*.

NB: After sanding, always carefully dust the surface.

* To protect the wood against UV, do not use «colourless» or «white» by itself outside as the finish coat. Always finish with 2 coloured coats.
** same manufacturer

LINITOP® is a trademark



Durieu S.A.
91070 BONDOUFLE - France
T. +33 (0)1 60 86 48 70
F. +33 (0)1 60 86 84 84
info@durieu.com
www.durieu.com

Durieu Coatings S.A. / N.V.
New Tech Center
Avenue Albert Einstein 2 A
1348 Louvain-La-Neuve
Belgique / België
T. +32 (0)10 420 090
F. +32 (0)10 420 099
info@durieucoatings.com
www.durieucoatings.com

0800 95 549

For further help or advice please contact us on:
Belgium: +32 (0)10 420090 - 0800 95549
France: +33 (0)1 60 86 48 70
or consult our site: www.linitop.com