

LINITOP®

WOODPRIM

Protection for new coniferous wood outdoors
Ideal for pressure treated wood



EXTERIOR



Priority to wood

Description	Water-based protection to stabilise new wood outdoors with variable dimensions such as coniferous wood, pressure treated or otherwise, during its first year of exposure.
Classification	Family 1 – Class 4a/7b2 (according to classifications NBT 22-003 and NFT 36-005).
Properties	<ul style="list-style-type: none"> • Stabilises and protects the wood during its first year of exposure to bad weather. • Essential for pressure treated wood. • Regulates the moisture and avoids resumptions of moisture while enabling the wood to gently deglaze. • Effective, including for those with surface glazing. • Considerably limits deformations and springing in the first months of exposure of the wood • Preserves its natural appearance while delaying greying. • Colourless, Woodprim is applied in a single coat. • After 6 to 12 months of exposure of the wood to bad weather yields a sound prepared surface before finishing with a saturating oil, stain, paint, varnish...
Basic uses	<ul style="list-style-type: none"> • Resinous wood, pressure treated or otherwise: douglas, larch, red cedar, spruce..., broadleaved wood. • Recommended for chalets, weatherboarding, shutters, doors, frames, railings, fencing, terraces, duckboards... • Applied directly, before or after fitting, to wood dry to the touch. Not suitable for wood already exposed to bad weather for several months.
Characteristics	<ul style="list-style-type: none"> • Composition: Modified acrylic and alkyd resins. • Density (at +20°C): 1.000 ± 0.05. • Flash point: Not classified as inflammable. • Viscosity: Fluid liquid. • Solid content: 5,5% ± 0.5. • VOC: EU limit value for this product (cat. A/f): 130 g/l (2010). This product contains a maximum of 11 g/l. • Packaging: 1 l and 2.5 l. • Shelf life: At least 2 years in the unused closed original packaging. • Storage conditions: Keep away from frost and high temperatures. • Appearance in the can: Brownly liquid. • Appearance of the dry product: Matt. • Colour: Colourless. • Tools: Brush, roller, spray gun. • Dilution: Ready to use. • Cleaning of the tools: Water + detergent. • Conditions of application: Respect the conditions and instructions stipulated by the product manufacturer. Do not apply at an ambient temperature of less than +10°C or greater than +30°C. 5 to 7 m²/l per coat. • Coverage: 5 to 7 m²/l per coat. • Drying (data at +20°C and 50% relative humidity): - Dust-dry: 3 to 4 hours. • Safety: Refer to the safety data sheet and the text given on the packaging, in accordance with the applicable legislation.

The information set out cons are purely illustrative and are not the responsibility of the manufacturer, the application of products not made under his supervision.

Priority to Wood

Surface preparation

- The wood must be dry, clean, in sound condition, free of any finishes and whose usage, nature, quality, treatments and preparation comply with the applicable standards and DTU (DTU 59.1).
- The wood must be dry to the touch before applying Woodprim.
- The inspection and preparation of the surface are the responsibility of the user.
- On new wood (or wood made bare) that is not durable and has not been treated with a preservative, it is recommended to first apply an insecticide, fungicide and anti-blue stain agent. Consult us.
- Depending on the surface and its condition, follow the instructions below.

Recommendations before application

- Shake the product well. Ready to use.
- Apply in the direction of the wood fibres, on wood free of any protective treatment/coating.
- Protect everything that does not have to be treated.
- Depending on the condition of the surface, follow the instructions in the Surface Preparation section.
- Apply between +10°C and +30°C. Do not apply in direct sunlight or on very hot wood.
- Do not apply if cold and/or rain are expected within 48 hours.

Directions for use

- Shake before and during application.
- Immediately after fitting the new wood on site, apply a generous coat of Woodprim to the entire surface to be treated. Pay particular attention to the spaces between the planks and the ends of them (butts).
- Leave Woodprim at least 6 months before applying a topcoat of the stain, saturating oil, varnish, paint type... (consult us).

Advice of the professionals

- Do not apply to waterproofed wood.
- To treat shingles, it is possible to soak them for 10 mn then let the product drain off.
- On grey wood exposed to bad weather for more than a year, apply Wood Cleaner* or Wood Oil Cleaner* if the wood has already been oiled.
- Always work from top to bottom on vertical surfaces.
- If a spray gun is used, smooth with a brush as you go along.

* same manufacturer

LINITOP® is a trademark



Durieu S.A.
91070 BONDOUFLE - France
 T. +33 (0)1 60 86 48 70
 F. +33 (0)1 60 86 84 84
 info@durieu.com
 www.durieu.com

Durieu Coatings S.A. / N.V.
New Tech Center
Avenue Albert Einstein 2 A
1348 Louvain-La-Neuve
Belgique / België
 T. +32 (0)10 420 090
 F. +32 (0)10 420 099
 info@durieucoatings.com
 www.durieucoatings.com

0800 95 549

For further help or advice please contact us on:
Belgium: +32 (0)10 420090 - 0800 95549
France: +33 (0)1 60 86 48 70
or consult our site: www.linitop.com