



LINITOP®

LINITOP COLOR MIX

Opaque satin-finish woodstain



priority to wood

Description	Water-based opaque woodstain.
Classification	Family I, class 7b2 (according to classifications NBT 22-003 and NFT 36-005).
Properties	<ul style="list-style-type: none"> Decorates, protects, resistant to dirt and washable. Fast drying, permeable to water vapour. Easy application: does not run. Stable colours. Protection against UV. Well rounded. Microporous, the wood structure remains visible.
Basic Uses	<ul style="list-style-type: none"> Indoors and outdoors. Woodwork (shutters, facades, eaves, frameworks...). Environments: rural, urban, industrial and maritime. On old coats of woodstains or paints (acrylic, alkyd) clean, adherent and roughened.
Characteristics	<ul style="list-style-type: none"> Composition: Density (at +20°C): Flash point: Viscosity: Solid content: Sheen: VOC: Packaging: Shelf life: Appearance in the can: Appearance of the dry product: Colours: Tools: Dilution: Cleaning of the tools: Conditions of application: Coverage: Drying (data at +20°C and 50% relative humidity): Safety: <p>Binder: acrylic resin. Primary solvent: water. 1.030 - 1.270 ± 0.005. Not classified inflammable. Semi-fluid liquid. 29.5 - 47.8% ± 2 (according to colour). Approx. 30% after 7 days drying. EU limit value for this product (cat. A/d): 130 g/l (2010). This product contains a maximum of 110 g/l VOC. 1 l, 2,5 l and 5 l. At least 2 years in the original unopened packaging, protect from frost. Variable depending on the colour.</p> <p>Satin. Available in 3 bases to be coloured (white, medium and clear). Brush, microfibre roller, spray gun and airless. Ready to use - must not be diluted except when applied with a spray gun: add approx. 10% water. With water. Respect the conditions and instructions specified by the producer of the product. Do not apply at an ambient temperature of less than +10°C or greater than +30°C. ± 12 m²/l per coat. - Touch dry: 2 h. - Recoatable: 8 h*. * In a cool and very humid atmosphere, the drying time and the before recoating may be longer than expected. Refer to the safety data sheet and the text stated on the packaging, in accordance with the applicable legislation.</p>

Surface preparation

- Apply to wood whose usage, nature, quality, treatments and preparation comply with the applicable standards and DTU (DTU 59.1). The inspection and preparation of the surface are the responsibility of the person applying the product.
- The wood must be clean, dry, sound, prepared (degrease, sand, dust if necessary), not frozen or rimed.

On new wood:

- Sand (grit 120) to encourage and optimise the opening of the pores.

On old wood:

- Expose the surface by sanding or stripping.

NB: After sanding, brush sanding, always meticulously dust the surface.

Recommendations before application

- Shake well before application.
- Do not apply at an ambient air and wood temperature of less than +10°C and greater than +30°C. The relative humidity should be of the order of 50 % for optimum drying.
- Comply with the applicable standards and DTU.
- Protect everything that does not have to be treated.
- The moisture of the wood should not be greater than 15%.

Directions for use

According to the surface condition:

New wood:

- After sanding, apply the protection.

Weathered wood:

- Clean with Wood Cleaner*, rinse and allow to dry.
- Sand (grit 120) if necessary.
- Apply the protection.

Darkened, oiled wood:

- Remove oil with Wood Oil Cleaner*, neutralise with Wood Cleaner* rinse and allow to dry.
- Sand (grit 120) if necessary.
- Apply the protection.

Wood to be stripped: consult us.

New wood system:

- Apply a generous coat of Linitop Prim & Finish* or Linitop Acryl Prim*.
- After drying complete with 2 coats of Linitop Color Mix.

Advice of the professionals

The Linitop Prim & Finish* or Linitop Acryl Prim* undercoat does not always have to be applied. You need to apply it to woodwork that is not yet impregnated. If the Linitop Prim & Finish* or Linitop Acryl Prim* should not be applied, it is preferable to dilute the 1st coat of Linitop Color Mix by 5 to 10 %.

Maintenance

Apply 1 to 2 coats of Linitop Color Mix depending on the condition of the surface, after having brushed or sanded.

NB: After sanding/brush sanding, always meticulously dust the surface.

* Same manufacturer

LINITOP® is a trademark



Durieu S.A.
91070 BONDOUFLE - France
T. +33 (0)1 60 86 48 70
F. +33 (0)1 60 86 84 84
info@durieu.com
www.durieu.com

Durieu Coatings S.A. / N.V.
New Tech Center
Avenue Albert Einstein 2 A
1348 Louvain-La-Neuve
Belgique / België
T. +32 (0)10 420 090
F. +32 (0)10 420 099
info@durieucoatings.com
www.durieucoatings.com

0800 95 549

For further help or advice please contact us on:
Belgium: +32 (0)10 420090 - 0800 95549
France: +33 (0)1 60 86 48 70
or consult our site: www.linitop.com